
















Terralys LF 16

Intended use

<input checked="" type="checkbox"/>		EN 13249 Construction of roads and other trafficked areas
<input checked="" type="checkbox"/>		EN 13250 Construction of railways
<input checked="" type="checkbox"/>		EN 13251 Earthworks, foundations and retaining structures
<input checked="" type="checkbox"/>		EN 13252 Drainage systems
<input checked="" type="checkbox"/>		EN 13253 Erosion control works
<input checked="" type="checkbox"/>		EN 13254 Construction of reservoirs and dams
<input checked="" type="checkbox"/>		EN 13255 Construction of canals
<input type="checkbox"/>		EN 13256 Construction of tunnels and underground structures
<input checked="" type="checkbox"/>		EN 13257 Solid waste disposal
<input checked="" type="checkbox"/>		EN 13265 Liquid waste disposal

Functions

<input checked="" type="checkbox"/>		Filtration
<input type="checkbox"/>		Reinforcement
<input checked="" type="checkbox"/>		Separation
<input type="checkbox"/>		Drainage
<input type="checkbox"/>		Protection

Durability

- To be covered within 1 month after installation.
- Predicted to be durable for a minimum of 25 years in natural soils with pH between 4 and 9 and soil temperatures lower than 25 °C.
- Terralys geotextiles consisting solely of polypropylene material have passed the oxidation test according to the EN ISO 13438. The minimum percentage retained strength is > 50 %.

Properties		Standard	Average	Tolerance	Unit
Tensile Strength	(MD)	EN ISO 10319	20,0	-2,6	kN/m
Tensile Strength	(CMD)	EN ISO 10319	20,0	-2,6	kN/m
Elongation	(MD)	EN ISO 10319	25,0	± 5,8	%
Elongation	(CMD)	EN ISO 10319	21,0	± 4,8	%
Dynamic Perforation Resistance		EN ISO 13433	16	+ 4	mm
Resistance to Static Puncture		EN ISO 12236	2,50	- 0,25	kN
Characteristic Opening Size		EN ISO 12956	150	± 45	µm
Water Permeability Normal to the Plane		EN ISO 11058	10	- 3	10 ⁻³ m/s
Mass per unit area*		EN ISO 9864	110,0	± 11,0	g/m ²
Fabric width *			on request	± 5	cm
Fabric length*			on request	± 2	%

* not mandated characteristics for CE-marking