






Terralys LF 360

Intended use	Functions
<input checked="" type="checkbox"/> 	<input checked="" type="checkbox"/>  Filtration
<input checked="" type="checkbox"/> 	<input type="checkbox"/>  Reinforcement
<input checked="" type="checkbox"/> 	<input checked="" type="checkbox"/>  Separation
<input checked="" type="checkbox"/> 	<input type="checkbox"/>  Drainage
<input checked="" type="checkbox"/> 	<input type="checkbox"/>  Protection
<input checked="" type="checkbox"/> 	
<input checked="" type="checkbox"/> 	
<input type="checkbox"/> 	
<input checked="" type="checkbox"/> 	
<input checked="" type="checkbox"/> 	

Durability

- To be covered within 1 month after installation.
- Predicted to be durable for a minimum of 25 years in natural soils with pH between 4 and 9 and soil temperatures lower than 25 °C.
- Terralys geotextiles consisting solely of polypropylene material have passed the oxidation test according to the EN ISO 13438. The minimum percentage retained strength is > 50 %.

Properties	Standard	Average	Tolerance	Unit
Tensile Strength (MD)	EN ISO 10319	21,00	- 3,0	kN/m
Tensile Strength (CMD)	EN ISO 10319	26,00	- 3,4	kN/m
Elongation (MD)	EN ISO 10319	26,0	± 6,0	%
Elongation (CMD)	EN ISO 10319	21,0	± 5,0	%
Dynamic Perforation Resistance	EN ISO 13433	12	+ 3	mm
Resistance to Static Puncture	EN ISO 12236	2,80	- 0,50	kN
Characteristic Opening Size	EN ISO 12956	200	± 60	µm
Water Permeability Normal to the Plane	EN ISO 11058	11	- 3	10 ⁻³ m/s
Mass per unit area *	EN ISO 9864	118	± 13	g/m ²
Fabric width *		on request	± 5	cm
Fabric length*		on request	± 2	%

* not mandated characteristics for CE-marking