
















# Terralys LF 46/29 W

## Intended use

<input checked="" type="checkbox"/>		<b>EN 13249</b> Construction of roads and other trafficked areas
<input checked="" type="checkbox"/>		<b>EN 13250</b> Construction of railways
<input checked="" type="checkbox"/>		<b>EN 13251</b> Earthworks, foundations and retaining structures
<input checked="" type="checkbox"/>		<b>EN 13252</b> Drainage systems
<input checked="" type="checkbox"/>		<b>EN 13253</b> Erosion control works
<input checked="" type="checkbox"/>		<b>EN 13254</b> Construction of reservoirs and dams
<input checked="" type="checkbox"/>		<b>EN 13255</b> Construction of canals
<input type="checkbox"/>		<b>EN 13256</b> Construction of tunnels and underground structures
<input checked="" type="checkbox"/>		<b>EN 13257</b> Solid waste disposal
<input checked="" type="checkbox"/>		<b>EN 13265</b> Liquid waste disposal

## Functions

<input checked="" type="checkbox"/>		<b>Filtration</b>
<input type="checkbox"/>		<b>Reinforcement</b>
<input checked="" type="checkbox"/>		<b>Separation</b>
<input type="checkbox"/>		<b>Drainage</b>
<input type="checkbox"/>		<b>Protection</b>

## Durability

- To be covered within 1 month after installation.
- Predicted to be durable for a minimum of 50 years for non-reinforcing applications in natural soils with pH between 4 and 9 and soil temperatures lower than 25 °C on the basis of the results of test method EN 13249:2014 + A1:2015 clause B.4.2.2.

Properties		Standard	Average	Tolerance	Unit
Tensile Strength	(MD)	EN ISO 10319	<b>29,00</b>	-4,00	kN/m
Tensile Strength	(CMD)	EN ISO 10319	<b>29,00</b>	-4,00	kN/m
Elongation	(MD)	EN ISO 10319	<b>24,0</b>	± 5,5	%
Elongation	(CMD)	EN ISO 10319	<b>13,0</b>	± 3,0	%
Dynamic Perforation Resistance		EN ISO 13433	<b>10</b>	+ 2	mm
Resistance to Static Puncture		EN ISO 12236	<b>4,3</b>	- 0,9	kN
Characteristic Opening Size		EN ISO 12956	<b>370</b>	± 111	µm
Water Permeability Normal to the Plane		EN ISO 11058	<b>120</b>	- 35	10 <sup>-3</sup> m/s
Mass per unit area *		EN ISO 9864	<b>200</b>	± 20	g/m <sup>2</sup>
Fabric width *			<b>on request</b>	± 5	cm
Fabric length*			<b>on request</b>	± 2	%

\* not mandated characteristics for CE-marking