Durapack WHTR67 C1 rPP

Packaging Textiles



Technical Textiles

PRODUCT SPECIFICATION

TYPICAL PROPERTIES	TEST METHOD	VALUE		UNIT	TOLERANCE
		WARP	WEFT		
TOTAL WEIGHT		67		g/m²	± 5 %
WIDTH		180 - 200 - 220 - 400		cm	± 2 cm

PRODUCT INFORMATION

TYPICAL PROPERTIES	TEST METHOD	VALUE		UNIT	TOLERANCE
		WARP	WEFT		
MATERIAL		PP	PP		
COUNT OF TAPES	ISO 7211/2	94	15	/10cm	± 2 %
BREAK ELONGATION	ISO 13934-1	15	10	%	± 20 %
TENSILE STRENGTH	ISO 13934-1	700	175	N/5cm	± 20 %
TISSUE WEIGHT	ISO 3801	42		g/m²	± 5 %
TISSUE COLOUR		white-transparent			
COATING MATERIAL		PP			
COATED SIDES		1			
COATING WEIGHT/SIDE	ISO 2286	25		g/m²	± 10 %
COATING COLOUR		transparent			
LENGTH		1000		m	± 2 %

ENVIRONMENTAL IMPACT CATEGORIES

PROPERTIES	TEST METHOD	VALUE	UNIT	TOLERANCE			
GLOBAL WARMING POTENTIAL	EN 15804 +A2	0.01036	kg CO2 eq./m²				
(Cradle-to-Gate)	LN 13604 TAZ	0,01030					
Commenced to the atom dead DD medication was used to and estimation in CO2 of 17.0/							

Compared to the standard PP packaging, you reach a reduction in CO2 of 17 %.



Accordingly QA-CER system 2

mentioning 30% recycled content (post-industrial waste)

This information is not to be taken as a warranty or representation for which we assume legal responsibility. It is offered solely for your consideration, investigation, verification and shall form no part of any contract with the customer.

DATASHEET 1125: version 5 date: 17/04/2024