Durapack WHTR74 C1 rPP

Packaging Textiles



Technical Textiles

PRODUCT SPECIFICATION

| TYPICAL PROPERTIES | TEST METHOD | VALUE | | UNIT | TOLERANCE |
|--------------------|-------------|------------------------------|------|------|-----------|
| | | WARP | WEFT | | |
| TOTAL WEIGHT | | 74 | | g/m² | ± 5 % |
| WIDTH | | 125 - 133 - 150 200 - 400 | | cm | ± 2 cm |

PRODUCT INFORMATION

| TYPICAL PROPERTIES | TEST METHOD | VALUE | | UNIT | TOLERANCE | | |
|-----------------------------|-------------|---|------|-------|-----------|--|--|
| | | WARP | WEFT | | | | |
| MATERIAL | | PP | PP | | | | |
| COUNT OF TAPES | ISO 7211/2 | 94 | 25 | /10cm | ± 2 % | | |
| BREAK ELONGATION | ISO 13934-1 | 15 | 10 | % | ± 20 % | | |
| TENSILE STRENGTH | ISO 13934-1 | 700 | 275 | N/5cm | ± 20 % | | |
| TISSUE WEIGHT | EN 3801 | 49 | | g/m² | ±5% | | |
| TISSUE COLOUR | | white-transparent | | | | | |
| COATING MATERIAL | | PP | | | | | |
| COATED SIDES | | 1 | | | | | |
| COATING WEIGHT/SIDE | ISO 2286 | 25 | | g/m² | ± 10 % | | |
| COATING COLOUR | | transparent | | | | | |
| LENGTH | | 1000 | | m | ± 2 % | | |
| RECYCLED COMPANY ADLYMERS | mentioni | Accordingly QA-CER system 2 mentioning 30% recycled content (post-industrial waste) | | | | | |

This information is not to be taken as a warranty or representation for which we assume legal responsibility. It is offered solely for your consideration, investigation, verification and shall form no part of any contract with the customer.

DATASHEET 1130 : version 2 date: 03/04/2024