

TECHNICAL DATASHEET

Terralys LF 68/68

Terralys LF 68/68 is a polypropylene woven slit film geotextile, manufactured into a dimensionally stable network, ensuring that filaments retain their relative positions.

Terralys LF 68/68 is inert to biological degradation, and resists most chemicals, alkali and acids encountered in natural soils.

Mechanical properties	Test method	MARV ENGLISH	MARV METRIC
Grab Tensile Strength (MD x CMD)	ASTM D4632	450 lbs x 315 lbs	2000 N x 1400 N
Grab Tensile Elongation (MD x CMD)	ASTM D4632	23 % x 16%	23 % x 16%
Trapezoid Tear Strength MD	ASTM D4533	190 lbs x 210 lbs	850 N x 950 N
CBR Puncture	ASTM D6241	1600 lbs	7000 N
Permittivity	ASTM D4491	0.20 sec ⁻¹	0.20 sec ⁻¹
Water Flow Rate	ASTM D4491	15 gal/min/ft ²	600 L/min/m ²
UV Resistance (500 hrs)	ASTM D4355	80 %	80 %

Descriptive characteristics	Test method	TYPICAL ENGLISH	TYPICAL METRIC
Mass per unit area	ASTM D5261	8.2 oz/y ²	278 g/m ²

Note: The values presented in the tables above are indicative, they are offered solely to provide possible suggestions. We reserve the right to alter the results of these materials without prior notice. As the installation and the conditions of use are beyond our control, Beaulieu Technical Textiles cannot accept responsibility for the performance of any of these products. The properties listed herein are provided as information only and in no way can create any warranty.